



UV ADHESIVE • CODE 1000

Krystal 1000

UV Adhesive

REF EWC/9021/07062016

ISSUED July 2016

REVIEWED June 2026

PAGE 1

PRODUCT DESCRIPTION

Krystal 1000 is a one component UV & visible light curable adhesive which is designed for bonding ABS, HIPS, PS, PC, PVC and Acrylic etc. This product is suitable for bonding applications that require high adhesion and clarity. This UV adhesive will polymerize under ultraviolet light (365nm) and cure within seconds when exposed to correct UV light source and intensity.

CHARACTERISTICS

- Ultra-clear
- Good thermal and shock resistance
- Good weather resistance

PHYSICAL PROPERTIES (UNCURED)

PROPERTIES	SPECIFICATION
Chemical Properties	Acrylic Resin
Appearance	Pale Yellow Liquid
Specific Gravity	1.23
Viscosity @ 25°C (S14 100 rpm)	650 - 1050
Solvent Content, %	0

TYPICAL PROPERTIES OF CURED MATERIAL

PROPERTIES	SPECIFICATION
Hardness, Shore D	65
Refractive Index	1.4825
Tensile Strength, Kg/cm ² (Acrylic to Acrylic)	108
Elongation @ 25°C, %	228
Glass Transition Temp, °C	-5
Temperature Range °C	-40 to 100

CURE SCHEDULE

PROPERTIES	SPECIFICATION
UV Light Intensity	1500 - 3000 mj/cm ²
Wavelength	365nm
Recommended Cure Time, seconds	10 - 15

STORAGE CONDITION

Store original container in a cool and dry area where it is not exposed to high heat or direct sunlight. Advise to store UV adhesive below 25°C.

PACKAGING SIZES

- 50ML Plastic Anti-UV Bottle
- 1 Liter Plastic Anti -UV Bottle

SHELF LIFE

This product has 1year shelf life when stored in original, unopened container between 15-25 °C, away from direct light sources.

HANDLING PRECAUTIONS

Some findings indicate a lack of potential for carcinogenicity with the compositions of by long term recurrent application to the skin. However, contact with skin is likely to produce mild transient reddening. It is important to remove adhesive from skin with soap and water thoroughly. Krystal 1000 is of moderate acute toxicity by swallowing. If swallowed, induce vomiting at once and call a physician. Avoid contact with eyes. In case of contact, flush with water for at least 15 minutes and get medical attention immediately. For specific information on this product, consult the Material Safety Data Sheet.

■ COMPLIANCE AND QUALITY

Made under the ISO 9001 quality management system of Vitrochem Technology. RoHS declarations and Safety Data Sheets are available on request.

Vitrochem Technology Pte Ltd

1, Bukit Batok Crescent, #05-40 WCEGA Plaza, Singapore 658064 · +65 6766 7191 · +65 6766 7187 · www.mightyloc.com

Data last reviewed **June 2026**.

All recommendations for the use of our products are based on the current state of our knowledge. The Buyer remains responsible for satisfying itself that the product is suitable for its intended process or purpose. Since we cannot control the application, use, or processing of the product, we accept no responsibility on that basis. Refer to the current controlled data sheet, or contact us, before production use.