ANAEROBIC ADHESIVES · CODE 71

Taftlock 71

Anaerobic Thread Locker

ISSUED Updated: Sept 2018 | REVIEWED June 2026 | PAGE 1

PRODUCT DESCRIPTION

TAFTLOCK 71 is a fast curing, high strength anaerobic thread locking compound ideal for bonding and sealing threads, and retaining of cylindrical parts. TAFTLOCK 71 exhibits high resistance to heat, vibrations, water, gases, oils, hydrocarbons and many chemicals.

ADVANTAGES

- Ideal for transmission and engine block studs, valve sets etc
- Ideal for fasteners up to 25 mm in diameter.
- Permanent high strength, eliminates the need for double nutting and welding.
- Effectively prevents corrosion and leakage.

ADHESIVE PROPERTIES

Composition:	Methacrylate Ester
Color:	Red
Viscosity:	500 cps at 25°C
(Brookfield RVT, Spindle 3 @ 20 rpm)	
Specific Gravity:	1.11
Flash Point:	>100 °C
Shelf Life:	2 years

CURING PROPERTIES

Handling Cure Time:	10 minutes
Functional Cure Time:	1 - 3 hours
Full Cure Time:	24 hours
Breakaway Torque, ISO 10964: (M10 steel nuts and bolts N.m)	31 N.m (310 kgf/cm)
Prevail Torque, ISO 10964: (3/8 × 16 steel nuts and bolts)	28 N.m (280 kgf/cm)
Temperature Range:	-55 to 150°C

PHYSICAL PROPERTIES

Coefficient of Thermal Expansion (ASTM D696, K-1)	80×10^{-6}
Coefficient of Thermal Conductivity (ASTM C 177, W/(m.k)	0.10
Specific Heat (kJ/kg.K)	0.30

CHEMICAL RESISTANCE

CHEMICAL	TEMPERATURE	% INITIAL STRENGTH RETAINED 500 HOURS	% INITIAL STRENGTH RETAINED 1'000 HOURS
Acetone	22°C	95	90
Ethanol	22°C	100	100
Motor Oil	125°C	95	95
Gasoline	22°C	100	100
Brake Fluid	22°C	100	100
Water / Glycol	87°C	90	80

APPLICATION METHOD

Surfaces should be dry, clean, and free of any contamination. Thread locker should be applied to the bolt in sufficient quantity to fill threads. TAFTLOCK 71 performs the best in thin bond gaps. This thread locker is specifically formulated to give controlled friction and torque/tension ratio during assembly.

STORAGE

Anaerobic adhesives shall be ideally stored in a cool, dry place in unopened containers at room temperature between 8°C to 25°C. Please do not return any unused material to its original container.

COMPLIANCE AND QUALITY

RoHS statements and Safety Data Sheets for this product are available on request. Contact the MightyLoc team and we will send the current documents.

Vitrochem Technology Pte Ltd

1, Bukit Batok Crescent, #05-40 WCEGA Plaza, Singapore 658064 · +65 6766 7191 · +65 6766 7187 · www.mightyloc.com

Data last reviewed **June 2026**.

All recommendations for the use of our products are based on the current state of our knowledge. The Buyer remains responsible for satisfying itself that the product is suitable for its intended process or purpose. Since we cannot control the application, use, or processing of the product, we accept no responsibility on that basis. Refer to the current controlled data sheet, or contact us, before production use.