



TECHNICAL DATA SHEET

Krystal 2000 UV Adhesive

July 2016

Product Description

Krystal 2000 is photo-curing UV adhesive that will polymerize under ultraviolet light (365nm) or with visible light (436nm). This fast cure adhesive will set and cure within seconds when exposed to correct UV light source and intensity. It will not turn yellow when exposed to high temperature at 80°C with good water and weather resistance. It bonds well to glass, acrylic, polycarbonate, ABS and some metals.

Characteristics

- Excellent clarity or transparency
- Non yellowing
- Good thermal and shock resistance
- Good weather resistance

Physical Properties (Uncured)

Properties	Specification
Chemical Properties	Acrylic Resin
Appearance	Clear Liquid
Viscosity @ 25°C (S14 100 rpm)	5000 - 7000
Solvent Content, %	0

Typical properties of cured material

Properties	Specification
Hardness, Shore D	67
Refractive Index	1.4788
Elongation @ 25°C, %	173
Glass Transition Temp, °C	-16
Temperature Range °C	-40 to 120

Cure Schedule

Properties	Specification
UV Light Intensity	1500 – 3000 mj/cm ²
Wavelength	365nm
Recommended Cure Time, seconds	10 - 15

EWC/GA006/07062016



VITROCHEM TECHNOLOGY

All recommendations for the use of our products, whether given by us in writing, verbally, or to be implied from the results of tests carried out by us, are based on the current state of our knowledge. Notwithstanding any such recommendations the Buyer shall remain responsible for satisfying himself that the products as supplied by us are suitable for his intended process or purpose. Since we cannot control the application, use or processing of the products, we cannot accept responsibility therefor. The Buyer shall ensure that the intended use of the products will not infringe any third party's intellectual property rights. We warrant that our products are free from defects in accordance with and subject to our general conditions of supply.



TECHNICAL DATA SHEET

Krystal 2000 UV Adhesive

July 2016

Storage Condition

Store original container in a cool and dry area where it is not exposed to high heat or direct sunlight. Advise to store UV adhesive below 25°C.

Packaging Sizes

50ML Plastic Anti-UV Bottle

1 Liter Plastic Anti -UV Bottle

Shelf Life

This product has 1year shelf life when stored in original, unopened container between 15-25 °C, away from direct light sources.

Handling Precautions

Some findings indicate a lack of potential for carcinogenicity with the compositions of by long term recurrent application to the skin. However, contact with skin is likely to produce mild transient reddening. It is important to remove adhesive from skin with soap and water thoroughly. Krystal 1000 is of moderate acute toxicity by swallowing. If swallowed, induce vomiting at once and call a physician. Avoid contact with eyes. In case of contact, flush with water for at least 15 minutes and get medical attention immediately. For specific information on this product, consult the Material Safety Data Sheet.

EWC/GA006/07062016



VITROCHEM TECHNOLOGY

All recommendations for the use of our products, whether given by us in writing, verbally, or to be implied from the results of tests carried out by us, are based on the current state of our knowledge. Notwithstanding any such recommendations the Buyer shall remain responsible for satisfying himself that the products as supplied by us are suitable for his intended process or purpose. Since we cannot control the application, use or processing of the products, we cannot accept responsibility therefor. The Buyer shall ensure that the intended use of the products will not infringe any third party's intellectual property rights. We warrant that our products are free from defects in accordance with and subject to our general conditions of supply.