



# Technical Data Sheet

August 2017

## 6221 POLYURETHANE SEALANT

### PRODUCT DESCRIPTION

TAFTFLEX 6221 is a one-component, moisture-curable, polyurethane-based, elastomeric adhesive sealant. After curing, it provides a permanently elastic bond to fasten materials with different coefficients of expansion.

### PRODUCT FEATURES

- Good Adhesion to a wide range of substrates.
- Cures rapidly to a permanently elastic consistency with excellent cut and tear resistance.
- Low odor, non-staining.
- Surface paintable with water, oil, and rubber based coatings.
- Non-corrosive.
- Provides shock resistance and vibration damping.
- Exhibits high recovery, making it ideal for sealing dynamically moving joints.
- Weather resistant.

### TYPICAL APPLICATION AREAS

- Vehicle bodies and cab construction including panels, underbody components, and roofing.
- Front and rear spoilers, auto trim, moldings, body seams, and welded joints.
- Waterproofing exterior lap seams in many applications, including truck trailers, RV's, metal roofs, window perimeters, grain bins and HVAC units.
- Waterproofing rivet seams.
- Sealing of exposed and concealed joints of aluminum, steel, coated metals, wood, roof rails, and door hinges in transport equipment.
- Sealing and caulking expansion joints, pre-cast concrete panel joints.

### SPECIFICATION

Item	Value
Chemical base	1-C polyurethane
Color	Black, white, grey
Cure mechanism	Moisture-curing
Density	1.15 ± 0.05 kg/l
Non-sag properties	Good
Application temperature	5°C -35°C
Skin formation time @ 23°C, 50%RH*	70 min.
Curing speed* @ 23°C, 50%RH	3.5mm/24 hrs.
Shore A hardness	40
Modulus at 100% (ISO 37)	Approx. 0.3 MPa
Modulus at break (ISO 37)	Approx. 1.4 MPa



Mightyloc and Taftflex is a registered trademark owned by Vitrochem Technology

All recommendations for the use of our products, whether given by us in writing, verbally, or to be implied from the results of tests carried out by us, are based on the current state of our knowledge. Notwithstanding any such recommendations the Buyer shall remain responsible for satisfying himself that the products as supplied by us are suitable for his intended process or purpose. Since we cannot control the application, use or processing of the products, we cannot accept responsibility therefor. The Buyer shall ensure that the intended use of the products will not infringe any third party's intellectual property rights. We warrant that our products are free from defects in accordance with and subject to our general conditions of supply.



# Technical Data Sheet

August 2017

## 6221 POLYURETHANE SEALANT

Item	Value
Elongation at break	600%
Tear Strength	>10 N/mm
Service temperature (permanent)	-40°C to +80°C

### APPLICATION METHOD

- **Cleaning:** Clean surface with a strong jet of compressed air, sandblast, or solvent to ensure the surface being clean, dry, free of oil, grease, and of sound quality.
- **Activating/Priming:** Activators and/or primers may be required to achieve optimal adhesion depending on the nature of substrates.
- **Application of sealant:** Cut tip to desired shape and size. Puncture airtight seal. Install with hand or power operated gun and extrude the sealant into the joint. Clean excess sealant using hard rubber plate or finger wet with soap solution.

### CAULKING

TAF FLEX 6221 can be applied by a manual or pneumatic gun. After application, use a putty knife to smooth the joint with soapy water. This product should be used within 24 hours of opening the cartridge or sausage; otherwise, the sealant could harden inside. Do not apply at a temperature under 5 °C. In cold weather, store the cartridges at about 20 °C before use. Avoid any contact with non-cured MS, hybrid PU or silicone sealants as well as with alcohols or ammonia during curing.

### PACKAGING STANDARD

310ml cartridge, 600ml sausage

### CLEANING METHOD

Always clean the bonding substrates with appropriate cleaning agent prior to applying the polyurethane adhesive. This will ensure good bonding integrity when fully cured.

### STORAGE CONDITIONS

Store polyurethane sealant in a cool and dry area (15-25°C), away from direct sunlight. Storing this product otherwise may reduce shelf life and affects physical properties adversely. Do not store the polyurethane for more than 30°C as it may affect the viscosity of the compound and making it difficult for caulking. This product has 12 months shelf life if stored at the recommended temperature.

### HANDLING PRECAUTION

- Refer to Safety Data Sheet (MSDS) before using this product.
- Always wear personal safety gears when handling this product. (Impervious gloves, eyes protection goggles, respiratory mask.)



Mightyloc and Taffflex is a registered trademark owned by Vitrochem Technology

All recommendations for the use of our products, whether given by us in writing, verbally, or to be implied from the results of tests carried out by us, are based on the current state of our knowledge. Notwithstanding any such recommendations the Buyer shall remain responsible for satisfying himself that the products as supplied by us are suitable for his intended process or purpose. Since we cannot control the application, use or processing of the products, we cannot accept responsibility therefor. The Buyer shall ensure that the intended use of the products will not infringe any third party's intellectual property rights. We warrant that our products are free from defects in accordance with and subject to our general conditions of supply.